



Activated Alumina JZ-K2

Description:

JZ-K2 activated alumina is specially designed. Compared with JZ-K1, with 20% increase of water adsorption and surface area.

Applications:

Air dryer/ Air separation systems

Specification:

Properties	Unit	JZ-K2	
Diameter	mm	3-5	4-6
Bulk Density	≥g/ml	0.68	0.67
Surface Area	≥m ² /g	360	360
Pore Volume	≥ml/g	0.38	0.36
Crush Strength	≥N/Pc	110	150
L.O.I.	≤%	8	8
Attrition Rate	≤%	0.3	0.3

Standard Package:

25 kg/woven bag
150 kg/steel drum

Attention:

The product as desiccant cannot be exposed in the open air and should be stored in dry condition with air-proof package.

CÔNG TY TNHH TM & DV CH VIỆT NAM

VP Giao Dịch : Số 73C/291/42 - Lạc Long Quân - Nghĩa Đô - Cầu Giấy - HN
Trạm bảo hành 24/7: Số 12 ngõ 190/5 - Thanh Am - Long Biên Hà Nội
CN Miền Nam: 150/10 - HT13, KP2, Hiệp Thành , Quận 12, Tp. Hồ Chí Minh
Điện thoại: 024.6.6868.111 Hotline: 0909.514.123

